Soft Ingot Iron Rod - Ø 25.4mm L 10mm

Grade: Soft Ingot Iron
Formula: Fe
Percentage Purity: 99.8%
Diameter: 25.4mm
Length: 10mm
Temper: As Drawn
CAS Number: 7439-89-6
UOM Code: 108-472-75
Legacy Code: FE007969
Distributor Code: GF10847275
SKU: 1000021165
Product Code: FE00-RD-000169

Material Properties for Metals

Atomic Properties

Element	Value
Atomic number	26
Crystal structure	Body centred cubic
Electronic structure	Ar 3d? $4s^2$
Valences shown	2, 3, 4, 6
Atomic weight(amu)	55.847
Thermal neutron absorption cross-section(Barns)	2.56
Photo-electric work function(eV)	4.4
Natural isotope distribution(Mass No./%)	58/ 0.3
Natural isotope distribution(Mass No./%)	57/ 2.1
Natural isotope distribution(Mass No./%)	56/ 91.8
Natural isotope distribution(Mass No./%)	54/ 5.8
Atomic radius - Goldschmidt(nm)	0.128
Ionisation potential(No./eV)	2/ 16.18
Ionisation potential(No./eV)	5/ 75.0
Ionisation potential(No./eV)	4/ 54.8
Ionisation potential(No./eV)	3/ 30.65
Ionisation potential(No./eV)	1/ 7.87
Ionisation potential(No./eV)	Jun-99

Mechanical Properties

Element	Value
Hardness - Mohs	04-5
Material condition	Polycrystalline
Poisson's ratio	0.293
Bulk modulus(GPa)	169.8
Tensile modulus(GPa)	211.4
Izod toughness(J m?¹)	8-16
Tensile strength(MPa)	180-210
Yield strength(MPa)	120-150

Electrical Properties

Element	Value
Electrical resistivity(µOhmcm)	10.1@20°C
Temperature coefficient(K?¹)	0.0065@0-100°C
Thermal emf against Pt (cold 0C - hot 100C)(mV)	1.98

Physical Properties

Element	Value
Boiling point(C)	2750
Density(gcm?³)	7.87@20°C

Thermal Properties

Element	Value
Melting point(C)	1535
Latent heat of evaporation(J g?¹)	6095
Latent heat of fusion(J g?¹)	272
Specific heat(J K?¹ kg?¹)	444@25°C
Thermal conductivity(W m?¹ K?¹)	80.4@0-100°C
Coefficient of thermal expansion(x10?? K?¹)	12.1@0-100°C