



## Physical properties of TPX® DX350

Highly recommended for paper coating extrusion, possible use for fibre extrusion

Physical Properties	Item	Test Condition	Unit	Test Method	Value	
Basic Properties	Density		kg/m <sup>3</sup>	ASTM-D1505	833	
	MFR	P=5kg, 260°C	g/10 min	ASTM-D1238	110	
	Melting Point	Peak Temp.	°C	JIS-K7121 (DSC method)	233	
	Water Absorption		%	ASTM-D570	<0.01	
Thermal Properties	Vicat Softening Point		°C	ASTM-D1525	169	
	Heat Distortion Temperature (HDT)	0.43 MPa	°C	ASTM-D648	124	
	Expansion Coefficient		10 <sup>-6</sup> K <sup>-1</sup>	ASTM-E831	1.17x10 <sup>-4</sup>	
Mechanical Properties @ 23°C	Yield Stress		MPa	ASTM-D638	29	
	Tensile Strength		MPa	ASTM-D638	25	
	Elongation at Break		%	ASTM-D638	14	
	Tensile Modulus		MPa	ASTM-D638	1800	
	Flexural Modulus		MPa	ASTM-D790	1500	
	Flexural Strength		MPa	ASTM-D790	41	
	Izod Impact Strength	With Notch		J/m	ASTM-D256	19
		Without Notch		KJ/m <sup>2</sup>	ASTM-D256	9
Rockwell Hardness	R Scale		-	ASTM-D785	87	
Optical Properties	Haze		%	ASTM-D1003	2.1	
	Transmittance		%	ASTM-D1003	93	
	Refractive Index		-	ASTM-D542	1.46	
Electrical Properties	Volume Resistivity		Ω . cm	ASTM-D257	>10 <sup>16</sup>	
	Dielectric Breakdown Voltage		kV/mm	ASTM-D149	65	
	Dielectric Constant		-	ASTM-D150	2.1	

### Notes:

MCI method 1 moulding temp: 310~330°C (depending on the grade)

MCI method 2 moulding temp: 260~280°C (depending on the grade)

All information and technical data are given as a guide only. Although every effort has been made to ensure that the information is correct, no warranty is given as to its completeness or accuracy.

**Goodfellow Cambridge Limited**  
Ermine Business Park  
Huntingdon, Cambridgeshire PE29 6WR  
Tel: +44 1480 424 800  
Fax: +44 1480 424 900  
Email: [tpx@goodfellow.com](mailto:tpx@goodfellow.com)  
Web: [www.goodfellow.com](http://www.goodfellow.com)