

# Niobium Disk

**Formula:** Nb

**Percentage Purity:** 99.9%

**Temper:** Annealed

**Thickness:** 0.25mm

**Diameter:** 4mm

**CAS Number:** 7440-03-1

**UOM Code:** 002-254-47

**SKU:** 1000000313-group

**Product Code:** NB00-FL-000260

## Material Properties for Metals

### Atomic Properties

Element	Value
Atomic number	41
Crystal structure	Body centred cubic
Electronic structure	Kr 4d <sup>4</sup> 5s <sup>1</sup>
Valences shown	2, 3, 4, 5
Atomic weight( amu )	92.9064
Thermal neutron absorption cross-section( Barns )	1.15
Photo-electric work function( eV )	4.3
Atomic radius - Goldschmidt( nm )	0.147
Ionisation potential( No./eV )	3/ 25.0
Ionisation potential( No./eV )	2/ 14.3
Ionisation potential( No./eV )	6/ 103
Ionisation potential( No./eV )	1/ 6.88
Ionisation potential( No./eV )	4/ 38.3
Ionisation potential( No./eV )	5/ 50.5

### Mechanical Properties

Element	Value
Material condition	Hard
Material condition	Soft
Poisson's ratio	0.397

<b>Element</b>	<b>Value</b>
Poisson's ratio	0.397
Bulk modulus( GPa )	170.3
Bulk modulus( GPa )	170.3
Tensile modulus( GPa )	104.9
Tensile modulus( GPa )	104.9
Izod toughness( J m <sup>-1</sup> )	10-120
Hardness - Vickers( kgf mm <sup>-2</sup> )	115
Hardness - Vickers( kgf mm <sup>-2</sup> )	160
Tensile strength( MPa )	330
Tensile strength( MPa )	585
Yield strength( MPa )	550
Yield strength( MPa )	240

## **Electrical Properties**

<b>Element</b>	<b>Value</b>
Electrical resistivity( $\mu\text{Ohmcm}$ )	16@20@20°C
Superconductivity critical temperature( K )	9.25
Temperature coefficient( K <sup>-1</sup> )	0.0026@0-100°C

## **Physical Properties**

<b>Element</b>	<b>Value</b>
Boiling point( C )	4742
Density( gcm <sup>-3</sup> )	8.57@20°C

## **Thermal Properties**

<b>Element</b>	<b>Value</b>
Melting point( C )	2468
Latent heat of evaporation( J g <sup>-1</sup> )	7360
Latent heat of fusion( J g <sup>-1</sup> )	290
Specific heat( J K <sup>-1</sup> kg <sup>-1</sup> )	268@25°C
Thermal conductivity( W m <sup>-1</sup> K <sup>-1</sup> )	53.7@0-100°C
Coefficient of thermal expansion( $\times 10^{-6}$ K <sup>-1</sup> )	7.2@0-100°C