

Monel® 400 Tube

Formula: Ni65/Cu33/Fe 2

Outside Diameter: 6.35mm

Wall Thickness: 1.5mm

Inside Diameter: 3.35mm

Length: 200mm

Temper: As Drawn

UOM Code: 003-983-25

SKU: 1000000512-group

Product Code: NI11-TB-000600

Material Properties for Alloys

Mechanical Properties

Element	Value
Hardness - Brinell	125-190
Elongation at break(%)	40
Modulus of elasticity(GPa)	185
Izod impact strength(J m ²)	110-140
Tensile strength(MPa)	550-950

Electrical Properties

Element	Value
Electrical resistivity(μOhmcm)	48-51
Temperature coefficient(K ⁻¹)	0.0019

Thermal Properties

Element	Value
Maximum use temperature in air(C)	450
Melting point(C)	1300-1350
Thermal conductivity(W m ⁻¹ K ⁻¹)	21.7@23°C
Coefficient of thermal expansion(x10 ⁻⁶ K ⁻¹)	13.9-14.1@20-100°C

Physical Properties

Element	Value
Density(gcm ³)	8.84