Lead Coil

Lead coil is a dense, malleable metal roll used for radiation shielding, EMI protection, and electrical insulation.
SKU: 1000001238-group
Product Code: PB00-FL-000111

Material Properties for Metals

Atomic Properties

Element	Value
Atomic number	82
Crystal structure	Face centred cubic
Electronic structure	Xe $4f^{1}$? $5d^{1}$? $6s^{2}$ $6p^{2}$
Valences shown	2, 4
Atomic weight(amu)	207.2
Thermal neutron absorption cross-section(Barns)	0.18
Photo-electric work function(eV)	4
Natural isotope distribution(Mass No./%)	207/ 22.1
Natural isotope distribution(Mass No./%)	208/ 52.4
Natural isotope distribution(Mass No./%)	206/ 24.1
Natural isotope distribution(Mass No./%)	204/ 1.4
Atomic radius - Goldschmidt(nm)	0.175
Ionisation potential(No./eV)	5/ 68.8
Ionisation potential(No./eV)	3/ 31.9
Ionisation potential(No./eV)	4/ 42.3
Ionisation potential(No./eV)	2/ 15.03
Ionisation potential(No./eV)	1/ 7.42

Mechanical Properties

Element	Value
Hardness - Mohs	1.5
Material condition	Polycrystalline
Material condition	Sand cast
Poisson's ratio	0.44
Poisson's ratio	0.44

Element	Value
Bulk modulus(GPa)	45.8
Bulk modulus(GPa)	45.8
Tensile modulus(GPa)	16.1
Tensile modulus(GPa)	16.1
Tensile strength(MPa)	12
Yield strength(MPa)	5.5

Electrical Properties

Element	Value
Electrical resistivity(µOhmcm)	20.6@20°C
Superconductivity critical temperature(K)	7.196
Temperature coefficient(K?¹)	0.0042@0-100°C
Thermal emf against Pt (cold 0C - hot 100C)(mV)	0.44

Physical Properties

Element	Value
Boiling point(C)	1740
Density(gcm?³)	11.35@20

Thermal Properties

Element	Value
Melting point(C)	327.5
Latent heat of evaporation(J g?¹)	862
Latent heat of fusion(J g?¹)	23.2
Specific heat(J K?¹ kg?¹)	159@25°C
Thermal conductivity(W m?¹ K?¹)	35.3@0-100°C
Coefficient of thermal expansion(x10?? K?¹)	29@0-100°C