

Palladium Foil

Formula: Pd

Percentage Purity: 99.95%

Thickness: 0.002mm

Length 1: 50mm

Length 2: 50mm

CAS Number: 7440-05-3

UOM Code: 013-137-61

SKU: 1000001706-group

Product Code: PD00-FL-000102

Material Properties for Precious Metals

Atomic Properties

Element	Value
Atomic number	46
Crystal structure	Face centred cubic
Electronic structure	Kr 4d ¹⁰
Valences shown	2, 3, 4
Atomic weight(amu)	106.42
Thermal neutron absorption cross-section(Barns)	6
Photo-electric work function(eV)	5
Natural isotope distribution(Mass No./%)	108/ 26.7
Natural isotope distribution(Mass No./%)	110/ 11.8
Natural isotope distribution(Mass No./%)	104/ 11.0
Natural isotope distribution(Mass No./%)	102/ 1.0
Natural isotope distribution(Mass No./%)	105/ 22.2
Natural isotope distribution(Mass No./%)	106/ 27.3
Atomic radius - Goldschmidt(nm)	0.137
Ionisation potential(No./eV)	1/ 8.3
Ionisation potential(No./eV)	2/ 19.4
Ionisation potential(No./eV)	3/ 32.9

Mechanical Properties

Element	Value
---------	-------

Material condition	Soft
Material condition	Hard
Poisson's ratio	0.39
Poisson's ratio	0.39
Bulk modulus(GPa)	187
Bulk modulus(GPa)	187
Tensile modulus(GPa)	121
Tensile modulus(GPa)	121
Hardness - Vickers(kgf mm ²)	40
Hardness - Vickers(kgf mm ²)	100
Tensile strength(MPa)	140-195
Tensile strength(MPa)	325
Yield strength(MPa)	205
Yield strength(MPa)	34.5

Electrical Properties

Element	Value
Electrical resistivity(μOhmcm)	10.8@20@20
Temperature coefficient(K ⁻¹)	0.0042@0-100
Thermal emf against Pt (cold 0C - hot 100C)(mV)	-0.57

Physical Properties

Element	Value
Boiling point(C)	3140
Density(gcm ³)	12@20°C

Thermal Properties

Element	Value
Melting point(C)	1554
Latent heat of evaporation(J g ⁻¹)	3398
Latent heat of fusion(J g ⁻¹)	157
Specific heat(J K ⁻¹ kg ⁻¹)	244@25
Thermal conductivity(W m ⁻¹ K ⁻¹)	71.8@0-100°C
Coefficient of thermal expansion($\times 10^{-6}$ K ⁻¹)	11@0-100