

Wollaston Platinum Spooled Wire

Grade: Wollaston
Formula: Pt
Percentage Purity: 99.9%
Product Shape: Spooled
Diameter: 0.005mm
Length: 0.1m
Coating: Silver coated
Outside Diameter: 0.025 - 0.1mm
CAS Number: 7440-06-4
UOM Code: 020-269-65

Wollaston wire, Silver coated.
 Overall outside diameter approx 0.025mm - 0.1mm.
 The weight shown is for the Platinum core only.
 The Silver outer sheath may be dissolved in aqueous 10% Nitric Acid. **SKU:** 1000002404-group
Product Code: PT00-WR-000105

Material Properties for Precious Metals

Atomic Properties

Element	Value
Atomic number	78
Crystal structure	Face centred cubic
Electronic structure	Xe 4f ¹⁴ 5d ⁹ 6s ¹
Valences shown	1,2,3,4
Atomic weight(amu)	195.08
Thermal neutron absorption cross-section(Barns)	9
Photo-electric work function(eV)	5.3
Natural isotope distribution(Mass No./%)	192/ 0.79
Natural isotope distribution(Mass No./%)	196/ 25.30
Natural isotope distribution(Mass No./%)	190/ 0.01
Natural isotope distribution(Mass No./%)	195/ 33.80
Natural isotope distribution(Mass No./%)	198/ 7.20
Natural isotope distribution(Mass No./%)	194/ 32.90
Atomic radius - Goldschmidt(nm)	0.138

Element	Value
Ionisation potential(No./eV)	1/ 9.0
Ionisation potential(No./eV)	2/ 18.6

Mechanical Properties

Element	Value
Material condition	Hard
Material condition	Soft
Poisson's ratio	0.39
Poisson's ratio	0.39
Bulk modulus(GPa)	276
Bulk modulus(GPa)	276
Tensile modulus(GPa)	170
Tensile modulus(GPa)	170
Hardness - Vickers(kgf mm ²)	40
Hardness - Vickers(kgf mm ²)	100
Tensile strength(MPa)	200-300
Tensile strength(MPa)	125-150
Yield strength(MPa)	14-35
Yield strength(MPa)	185

Electrical Properties

Element	Value
Electrical resistivity(μOhmcm)	10.58@20@20°C
Temperature coefficient(K ⁻¹)	0.00392@0-100°C

Physical Properties

Element	Value
Boiling point(C)	3827
Density(gcm ³)	21.45@20°C

Thermal Properties

Element	Value
Melting point(C)	1772
Latent heat of evaporation(J g ⁻¹)	2405
Latent heat of fusion(J g ⁻¹)	101
Specific heat(J K ⁻¹ kg ⁻¹)	133@025°C
Thermal conductivity(W m ⁻¹ K ⁻¹)	71.6@0-100°C
Coefficient of thermal expansion($\times 10^{-6}$ K ⁻¹)	9@0-100