

Indium Foil (Light Tight)

Formula: In

Percentage Purity: 99.999%

Temper: As Rolled

Thickness: 0.2mm

Length 1: 25mm

Length 2: 25mm

CAS Number: 7440-74-6

UOM Code: 026-393-69

SKU: 1000003131-group

Product Code: IN00-FL-000360

Material Properties for Metals

Atomic Properties

Element	Value
Atomic number	49
Crystal structure	Face centred tetragonal
Electronic structure	Kr 4d ¹⁰ 5s ² 5p ¹
Valences shown	1, 2, 3
Atomic weight(amu)	114.82
Thermal neutron absorption cross-section(Barns)	194
Photo-electric work function(eV)	4.12
Natural isotope distribution(Mass No./%)	113/ 4.3
Natural isotope distribution(Mass No./%)	115/ 95.7
Atomic radius - Goldschmidt(nm)	0.157
Ionisation potential(No./eV)	3/ 28.0
Ionisation potential(No./eV)	Apr-54
Ionisation potential(No./eV)	2/ 18.9
Ionisation potential(No./eV)	1/ 5.79

Mechanical Properties

Element	Value
Material condition	Polycrystalline
Material condition	Soft

Element	Value
Poisson's ratio	0.45
Poisson's ratio	0.45
Bulk modulus(GPa)	35.3
Bulk modulus(GPa)	35.3
Tensile modulus(GPa)	10.6
Tensile modulus(GPa)	10.6
Hardness - Vickers(kgf mm ²)	10
Tensile strength(MPa)	2.6-4.5

Electrical Properties

Element	Value
Electrical resistivity(μOhmcm)	8.8@20@20°C
Superconductivity critical temperature(K)	3.41
Temperature coefficient(K ⁻¹)	0.0052@0-100°C
Thermal emf against Pt (cold 0C - hot 100C)(mV)	0.69

Physical Properties

Element	Value
Boiling point(C)	2080
Density(gcm ³)	7.3@20°C

Thermal Properties

Element	Value
Melting point(C)	156.6
Latent heat of evaporation(J g ⁻¹)	2024
Latent heat of fusion(J g ⁻¹)	28.5
Specific heat(J K ⁻¹ kg ⁻¹)	234@25°C
Thermal conductivity(W m ⁻¹ K ⁻¹)	81.8@0-100°C
Coefficient of thermal expansion($\times 10^{-6}$ K ⁻¹)	24.8@0-100°C