

# PET Metallized Film with Aluminum - 1 Ohms/Square Coil

**Formula:** Polyester, PET, PETP  
**Metallised With:** Aluminium - 1 Ohms/Square  
**Thickness:** 0.012mm  
**Coil Width:** 350mm  
**Length:** 20m  
**Surface Finish:** Metallised On Both Sides  
**CAS Number:** 25038-59-9  
**UOM Code:** 043-302-57  
**SKU:** 1000005975-group  
**Product Code:** ES30-MZ-000114

## Material Properties for Polymers

### Chemical Resistance

Element	Value
Acids - concentrated	Good-Poor
Acids - dilute	Good
Alcohols	Good
Alkalis	Poor
Aromatic hydrocarbons	Good-Fair
Greases and Oils	Good
Halogenated Hydrocarbons	Good-Poor
Halogens	Fair-Poor
Ketones	Good-Fair

### Mechanical Properties

Element	Value
Coefficient of friction	0.2-0.4
Hardness - Rockwell	M94-101
Poisson's ratio	0.37-0.44
Tensile modulus( GPa )	02-Apr
Izod impact strength( J m <sup>-1</sup> )	13-35

<b>Element</b>	<b>Value</b>
Tensile strength( MPa )	80, for biax film 190-260

## **Electrical Properties**

<b>Element</b>	<b>Value</b>
Dielectric constant @ 1MHz	3
Dissipation factor @ 1kHz	0.002
Dielectric strength( kV mm <sup>-1</sup> )	17
Surface resistivity( Ohm/sq )	10 <sup>13</sup>
Volume resistivity( Ohmcm )	>10 <sup>12</sup>

## **Physical Properties**

<b>Element</b>	<b>Value</b>
Flammability	HB
Radiation resistance	Good
Refractive index	1.58-1.64
Resistance to Ultra-violet	Fair?
Limiting oxygen index( % )	21
Water absorption - equilibrium( % )	0.7
Water absorption - over 24 hours( % )	0.1
Density( gcm <sup>-3</sup> )	1.3-1.4

## **Thermal Properties**

<b>Element</b>	<b>Value</b>
Heat-deflection temperature - 0.45MPa( C )	115
Heat-deflection temperature - 1.8MPa( C )	80
Lower working temperature( C )	20
Upper working temperature( C )	115-170
Specific heat( J K <sup>-1</sup> kg <sup>-1</sup> )	1200-1350
Thermal conductivity( W m <sup>-1</sup> K <sup>-1</sup> )	0.15-0.4@23°C
Coefficient of thermal expansion( x10 <sup>-4</sup> K <sup>-1</sup> )	20-80