

# Silver Disk Single Crystal - T 3mm Ø 5mm

**Formula:** Ag  
**Percentage Purity:** 99.999%  
**Thickness:** 3mm  
**Diameter:** 5mm  
**Orientation:** -111  
**Orientation Accuracy:** = 1°  
**Polish:** Polished  
**Surface Finish:** = 0.03µm Ra  
**CAS Number:** 7440-22-4  
**UOM Code:** 295-223-15  
**Legacy Code:** AG0020DN  
**Distributor Code:** GF29522315  
**SKU:** 1000013540  
**Product Code:** AG00-SC-000352

## Material Properties for Precious Metals

### Atomic Properties

Element	Value
Atomic number	47
Crystal structure	Face centred cubic
Electronic structure	Kr 4d <sup>10</sup> 5s <sup>1</sup>
Valences shown	1-2,2
Atomic weight( amu )	107.8682
Thermal neutron absorption cross-section( Barns )	63.8
Photo-electric work function( eV )	4.7
Natural isotope distribution( Mass No./% )	107/ 51.83
Natural isotope distribution( Mass No./% )	109/ 48.17
Atomic radius - Goldschmidt( nm )	0.144
Ionisation potential( No./eV )	2/ 21.5
Ionisation potential( No./eV )	1/ 7.58
Ionisation potential( No./eV )	3/ 34.8

### Mechanical Properties

Element	Value
---------	-------

Material condition	Hard
Material condition	Soft
Poisson's ratio	0.367
Poisson's ratio	0.367
Bulk modulus( GPa )	103.6
Bulk modulus( GPa )	103.6
Tensile modulus( GPa )	82.7
Tensile modulus( GPa )	82.7
Izod toughness( J m <sup>2</sup> )	5
Hardness - Vickers( kgf mm <sup>2</sup> )	95
Hardness - Vickers( kgf mm <sup>2</sup> )	25
Tensile strength( MPa )	330
Tensile strength( MPa )	172

## Electrical Properties

Element	Value
Electrical resistivity( $\mu\text{Ohmcm}$ )	1.63@20°C
Temperature coefficient( K <sup>-1</sup> )	0.0041@0-100°C
Thermal emf against Pt (cold 0C - hot 100C)( mV )	0.74

## Physical Properties

Element	Value
Boiling point( C )	2212
Density( gcm <sup>3</sup> )	10.5@20°C

## Thermal Properties

Element	Value
Melting point( C )	961.9
Latent heat of evaporation( J g <sup>-1</sup> )	2390
Latent heat of fusion( J g <sup>-1</sup> )	103
Specific heat( J K <sup>-1</sup> kg <sup>-1</sup> )	237@25°C
Thermal conductivity( W m <sup>-1</sup> K <sup>-1</sup> )	429@0-100°C
Coefficient of thermal expansion( $\times 10^{-6}$ K <sup>-1</sup> )	19.1@0-100°C