

DuPont™ Nomex® T410 Polyaramid Film (Polymetaphenylene isophthalamide)

Grade: DuPont™ Nomex® T410

Formula: Polymetaphenylene isophthalamide

Thickness: 0.13mm

Length 1: 10mm

Length 2: 10mm

Production Method: Calendered Paper

UOM Code: 453-508-65

SKU: 1000029729-group

Product Code: AR31-FM-000135

Material Properties for Polymers

Chemical Resistance

Element	Value
Acids - concentrated	Poor
Acids - dilute	Good-Fair
Alcohols	Good
Alkalis	Good-Poor
Aromatic hydrocarbons	Good
Greases and Oils	Good
Halogenated Hydrocarbons	Good
Ketones	Good

Electrical Properties

Element	Value
Dielectric constant @ 1kHz	2.3
Dielectric strength(kV mm ⁻¹)	32
Volume resistivity(Ohmcm)	6x10 ¹⁷

Physical Properties

Element	Value
---------	-------

Radiation resistance	Good
Limiting oxygen index(%)	29
Water absorption - equilibrium(%)	9
Water absorption - over 24 hours(%)	0.08
Density(gcm ³)	1.38

Mechanical Properties

Element	Value
Elongation at break(%)	9
Izod impact strength(J m ⁻¹)	533unnotched
Tensile strength(MPa)	1800-3900

Thermal Properties

Element	Value
Heat-deflection temperature - 1.8MPa(C)	149
Upper working temperature(C)	200-300
Specific heat(J K ⁻¹ kg ⁻¹)	1200
Thermal conductivity(W m ⁻¹ K ⁻¹)	0.13@23°C
Coefficient of thermal expansion(x10 ⁻⁴ K ⁻¹)	20