

Copper Foil - T 0.007mm 100mm x 100mm

Formula: Cu

Percentage Purity: 99.97%

Thickness: 0.007mm

Length 1: 100mm

Length 2: 100mm

CAS Number: 7440-50-8

UOM Code: 124-374-01

Legacy Code: CU000170

Distributor Code: GF12437401

SKU: 1000034176

Product Code: CU00-FL-000170

Material Properties for Metals

Atomic Properties

Element	Value
Atomic number	29
Crystal structure	Face centred cubic
Electronic structure	Ar 3d ¹⁰ 4s ¹
Valences shown	1, 2
Atomic weight(amu)	63.546
Thermal neutron absorption cross-section(Barns)	3.8
Photo-electric work function(eV)	4.5
Natural isotope distribution(Mass No./%)	65/ 30.8
Natural isotope distribution(Mass No./%)	63/ 69.2
Atomic radius - Goldschmidt(nm)	0.128
Ionisation potential(No./eV)	4/ 55.2
Ionisation potential(No./eV)	6/ 103
Ionisation potential(No./eV)	1/ 7.73
Ionisation potential(No./eV)	5/ 79.9
Ionisation potential(No./eV)	3/ 36.8
Ionisation potential(No./eV)	2/ 20.29

Mechanical Properties

Element	Value
Material condition	Soft
Material condition	Hard
Poisson's ratio	0.343
Poisson's ratio	0.343
Bulk modulus(GPa)	137.8
Bulk modulus(GPa)	137.8
Tensile modulus(GPa)	129.8
Tensile modulus(GPa)	129.8
Izod toughness(J m ⁻¹)	68
Izod toughness(J m ⁻¹)	58
Hardness - Vickers(kgf mm ⁻²)	87
Hardness - Vickers(kgf mm ⁻²)	49
Tensile strength(MPa)	314
Tensile strength(MPa)	224
Yield strength(MPa)	270
Yield strength(MPa)	54

Electrical Properties

Element	Value
Electrical resistivity(μOhmcm)	1.69@20°C
Temperature coefficient(K ⁻¹)	0.0043@0-100°C
Thermal emf against Pt (cold 0C - hot 100C)(mV)	0.76

Physical Properties

Element	Value
Boiling point(C)	2567
Density(gcm ⁻³)	8.96@20°C

Thermal Properties

Element	Value
Melting point(C)	1083
Latent heat of evaporation(J g ⁻¹)	4796
Latent heat of fusion(J g ⁻¹)	205
Specific heat(J K ⁻¹ kg ⁻¹)	385@25°C
Thermal conductivity(W m ⁻¹ K ⁻¹)	401@0-100°C
Coefficient of thermal expansion($\times 10^{-6}$ K ⁻¹)	17@0-100°C