Molybdenum Hexagonal Bolt

Molybdenum hexagonal bolt offers strength, thermal stability, and corrosion resistance for furnace assemblies, vacuum systems, and reactor components. **SKU:** 1000036315-group
Product Code: MO00-BT-000130

Material Properties for Metals

Atomic Properties

Element	Value
Atomic number	42
Crystal structure	Body centred cubic
Electronic structure	Kr 4d? $5s^1$
Valences shown	2, 3, 4, 5, 6
Atomic weight(amu)	95.94
Thermal neutron absorption cross-section(Barns)	2.65
Photo-electric work function(eV)	4.2
Natural isotope distribution(Mass No./%)	95/ 15.9
Natural isotope distribution(Mass No./%)	96/ 16.7
Natural isotope distribution(Mass No./%)	98/ 24.1
Natural isotope distribution(Mass No./%)	97/ 9.6
Natural isotope distribution(Mass No./%)	92/ 14.8
Natural isotope distribution(Mass No./%)	94/ 9.3
Natural isotope distribution(Mass No./%)	100/ 9.6
Atomic radius - Goldschmidt(nm)	0.14
Ionisation potential(No./eV)	2/ 16.15
Ionisation potential(No./eV)	5/ 61.2
Ionisation potential(No./eV)	68
Ionisation potential(No./eV)	1/ 7.10
Ionisation potential(No./eV)	3/ 27.2
Ionisation potential(No./eV)	4/ 46.4

Mechanical Properties

Element	Value
Material condition	Hard

Element	Value
Material condition	Soft
Poisson's ratio	0.293
Poisson's ratio	0.293
Bulk modulus(GPa)	261.2
Bulk modulus(GPa)	261.2
Tensile modulus(GPa)	324.8
Tensile modulus(GPa)	324.8
Hardness - Vickers(kgf mm?²)	250
Hardness - Vickers(kgf mm?²)	200
Tensile strength(MPa)	485-550
Tensile strength(MPa)	620-690
Yield strength(MPa)	550
Yield strength(MPa)	415-450

Electrical Properties

Element	Value
Electrical resistivity(µOhmcm)	5.7@20°C
Superconductivity critical temperature(K)	0.915
Temperature coefficient(K?¹)	0.00435@0-100°C
Thermal emf against Pt (cold 0C - hot 100C)(mV)	1.45

Physical Properties

Element	Value
Boiling point(C)	4612
Density(gcm?³)	10.22@20°C

Thermal Properties

Element	Value
Melting point(C)	2617
Latent heat of evaporation(J g?¹)	6153
Latent heat of fusion(J g?¹)	290
Specific heat(J K?¹ kg?¹)	251@25°C
Thermal conductivity(W m?¹ K?¹)	138@0-100°C
Coefficient of thermal expansion(x10?? K?¹)	5.1@0-100°C