

Impact-modified PMMA Disk

Grade: Impact Modified

Formula: PMMA, Acrylic

Thickness: 0.25mm

Diameter: 12.7mm

Production Method: Extruded

Transparency: Clear/Transparent

CAS Number: 9011-14-7

UOM Code: 130-530-61

SKU: 1000037756-group

Product Code: ME30-SH-000105

Material Properties for Polymers

Physical Properties

Element	Value
Abbe number	57.2
Flammability	HB
Radiation resistance	Fair
Refractive index	1.49
Resistance to Ultra-violet	Good
Limiting oxygen index(%)	17-20
Water absorption - over 24 hours(%)	0.2
Density(gcm ³)	1.19

Chemical Resistance

Element	Value
Acids - concentrated	Good-Poor
Acids - dilute	Good-Poor
Alcohols	Good-Poor
Alkalis	Good
Aromatic hydrocarbons	Poor
Greases and Oils	Good
Halogenated Hydrocarbons	Poor
Halogens	Poor

Element	Value
Ketones	Poor

Electrical Properties

Element	Value
Dielectric constant @ 1MHz	2.6
Dissipation factor @ 1MHz	0.014
Dielectric strength(kV mm ⁻¹)	15
Surface resistivity(Ohm/sq)	10 ¹²
Volume resistivity(Ohmcm)	2-14 x 10 ¹²

Mechanical Properties

Element	Value
Hardness - Rockwell	M92-100
Poisson's ratio	0.35-0.4
Elongation at break(%)	2.5-4
Tensile modulus(GPa)	2.4-3.3
Izod impact strength(J m ^{-1/2})	16-32
Tensile strength(MPa)	80

Thermal Properties

Element	Value
Heat-deflection temperature - 0.45MPa(C)	105
Heat-deflection temperature - 1.8MPa(C)	95
Lower working temperature(C)	-40
Upper working temperature(C)	50-90
Specific heat(J K ⁻¹ kg ⁻¹)	1400-1500
Thermal conductivity(W m ⁻¹ K ⁻¹)	0.17-0.19@23°C
Coefficient of thermal expansion(x10 ⁻⁵ K ⁻¹)	70-77