

Polyester Iron Insulated Wire

Formula: Fe

Conductor Diameter: 0.25mm

Insulation: Polyester

Insulation Thickness: 0.01mm

Length: 0.1m

CAS Number: 7439-89-6

UOM Code: 149-398-05

SKU: 1000050042-group

Product Code: FE00-SW-000120

Material Properties for Metals

Atomic Properties

| Element | Value |
|---|------------------------------------|
| Atomic number | 26 |
| Crystal structure | Body centred cubic |
| Electronic structure | Ar 3d ⁶ 4s ² |
| Valences shown | 2, 3, 4, 6 |
| Atomic weight(amu) | 55.847 |
| Thermal neutron absorption cross-section(Barns) | 2.56 |
| Photo-electric work function(eV) | 4.4 |
| Natural isotope distribution(Mass No./%) | 58/ 0.3 |
| Natural isotope distribution(Mass No./%) | 57/ 2.1 |
| Natural isotope distribution(Mass No./%) | 56/ 91.8 |
| Natural isotope distribution(Mass No./%) | 54/ 5.8 |
| Atomic radius - Goldschmidt(nm) | 0.128 |
| Ionisation potential(No./eV) | 2/ 16.18 |
| Ionisation potential(No./eV) | 5/ 75.0 |
| Ionisation potential(No./eV) | 4/ 54.8 |
| Ionisation potential(No./eV) | 3/ 30.65 |
| Ionisation potential(No./eV) | 1/ 7.87 |
| Ionisation potential(No./eV) | Jun-99 |

Mechanical Properties

| Element | Value |
|-------------------------------------|-----------------|
| Hardness - Mohs | 04-May |
| Material condition | Polycrystalline |
| Poisson's ratio | 0.293 |
| Bulk modulus(GPa) | 169.8 |
| Tensile modulus(GPa) | 211.4 |
| Izod toughness(J m ⁻¹) | Aug-16 |
| Tensile strength(MPa) | 180-210 |
| Yield strength(MPa) | 120-150 |

Electrical Properties

| Element | Value |
|---|----------------|
| Electrical resistivity(μOhmcm) | 10.1@20@20°C |
| Temperature coefficient(K ⁻¹) | 0.0065@0-100°C |
| Thermal emf against Pt (cold 0C - hot 100C)(mV) | 1.98 |

Physical Properties

| Element | Value |
|------------------------------|--------------|
| Boiling point(C) | 2750 |
| Density(gcm ⁻³) | 7.87@20°C |

Thermal Properties

| Element | Value |
|--|--------------|
| Melting point(C) | 1535 |
| Latent heat of evaporation(J g ⁻¹) | 6095 |
| Latent heat of fusion(J g ⁻¹) | 272 |
| Specific heat(J K ⁻¹ kg ⁻¹) | 444@25°C |
| Thermal conductivity(W m ⁻¹ K ⁻¹) | 80.4@0-100°C |
| Coefficient of thermal expansion($\times 10^{-6}$ K ⁻¹) | 12.1@0-100°C |