

Nickel/Iron Alloy Sputtering Target (Ni80/Fe20)

Formula: Ni80/Fe20

Thickness: 1mm

Diameter: 50mm

UOM Code: 979-504-71

SKU: 1000161155-group

Product Code: NI29-ST-000100

Material Properties for Alloys

Magnetic Properties

Element	Value
Initial permeability	30000
Maximum permeability	400000
Coercivity (Hc)(A m ⁻¹)	0.02
Curie temperature(C)	460
Saturation flux density(T)	0.77

Mechanical Properties

Element	Value
Elongation at break(%)	38
Tensile strength(MPa)	930

Electrical Properties

Element	Value
Electrical resistivity(μOhmcm)	62
Temperature coefficient(K ⁻¹)	-

Thermal Properties

Element	Value
Melting point(C)	1445
Thermal conductivity(W m ⁻¹ K ⁻¹)	34.6@23°C
Coefficient of thermal expansion(x10 ⁻⁶ K ⁻¹)	12.9@20-100°C