

Gold Balls

Formula: Au

Percentage Purity: 99.99%

Diameter: 0.56mm

Quantity: 10 Pcs

UOM Code: 476-980-63

SKU: 1000225212-group

Product Code: AU00-SP-000146

Material Properties for Precious Metals

Atomic Properties

| Element | Value |
|---|--|
| Atomic number | 79 |
| Crystal structure | Face centred cubic |
| Electronic structure | Xe 4f ¹⁴ 5d ¹⁰ 6s ¹ |
| Valences shown | 1,3 |
| Atomic weight(amu) | 196.9665 |
| Thermal neutron absorption cross-section(Barns) | 98.8 |
| Photo-electric work function(eV) | 4.8 |
| Atomic radius - Goldschmidt(nm) | 0.144 |
| Ionisation potential(No./eV) | 1/ 9.22 |
| Ionisation potential(No./eV) | 2/ 20.5 |

Mechanical Properties

| Element | Value |
|------------------------|-------|
| Material condition | Soft |
| Material condition | Hard |
| Poisson's ratio | 0.42 |
| Poisson's ratio | 0.42 |
| Bulk modulus(GPa) | 171 |
| Bulk modulus(GPa) | 171 |
| Tensile modulus(GPa) | 78.5 |
| Tensile modulus(GPa) | 78.5 |

| Element | Value |
|---|--------------|
| Hardness - Vickers(kgf mm ²) | 20-30 |
| Hardness - Vickers(kgf mm ²) | 60 |
| Tensile strength(MPa) | 130 |
| Tensile strength(MPa) | 220 |
| Yield strength(MPa) | 205 |
| Yield strength(MPa) | - |

Electrical Properties

| Element | Value |
|---|---------------|
| Electrical resistivity(μOhmcm) | 2.20@20@20°C |
| Temperature coefficient(K ⁻¹) | 0.004@0-100°C |
| Thermal emf against Pt (cold 0C - hot 100C)(mV) | 0.74 |

Physical Properties

| Element | Value |
|-----------------------------|--------------|
| Boiling point(C) | 3080 |
| Density(gcm ³) | 19.3@20°C |

Thermal Properties

| Element | Value |
|--|--------------|
| Melting point(C) | 1064.4 |
| Latent heat of evaporation(J g ⁻¹) | 1738 |
| Latent heat of fusion(J g ⁻¹) | 64.9 |
| Specific heat(J K ⁻¹ kg ⁻¹) | 129@25°C |
| Thermal conductivity(W m ⁻¹ K ⁻¹) | 318@0-100°C |
| Coefficient of thermal expansion($\times 10^{-6}$ K ⁻¹) | 14.1@0-100°C |